

A History of Organotin Compounds Used as Catalysts

Why they became important, how they work, where they are added, and why regulation differs among organotin compounds¹

In brief

Organotin catalysts became important because very small additions can sharply accelerate difficult condensation, cross-linking and polyaddition reactions while providing useful selectivity and predictable cure. Their best-established industrial roles include cathodic electrodeposition (e-coat), polyurethane manufacture, coatings, adhesives, sealants and elastomers (CASE), room-temperature-vulcanized (RTV) silicones, and moisture-curing hybrid polymers such as MS and SPUR systems. The catalyst is generally added during resin manufacture or final formulation, before the heat-, moisture- or reactant-triggered cure step. Modern regulation must distinguish among specific dibutyltin and dioctyltin substances and among industrial, professional and consumer uses; the word “organotin” does not identify a single hazard or regulatory status. ^[1-7]

1. Why catalysts are needed in polymer and coating systems

Many important polymer-forming and cross-linking reactions are thermodynamically favourable but too slow, too temperature-dependent or insufficiently selective to be practical without catalysis. In polyurethane chemistry, for example, the key reaction is addition of an alcohol or polyol to an isocyanate to form a urethane linkage. In moisture-curing silicones and silane-terminated hybrid polymers, alkoxy silane or related groups must hydrolyse and condense fast enough to develop a useful skin time and through-cure. In polyester, alkyd and specialty-resin manufacture, esterification and transesterification must reach high conversion without excessive side reactions, colour formation or equipment corrosion. ^{[1][2][4]}

Organotin compounds became valuable because the tin centre can function as a Lewis acid and, depending on the ligand and reaction medium, can also form reactive tin-alkoxide or stannoxane species. This dual ability allows them to activate electrophilic centres such as isocyanates or carbonyl groups while organizing the reacting alcohol or silanol near the reaction site. The practical result can be a large increase in reaction rate at low catalyst loading, often with good control of gelation, cure and final properties. ^{[1][2][3]}

For industrial users, catalyst choice is not simply a question of maximum speed. Pot life, latency, hydrolytic stability, compatibility, bake schedule, moisture sensitivity, substrate, solvent polarity and the balance between desired and competing reactions all matter. Dibutyltin mercaptoacetate, for example, can provide delayed urethane reactivity, while carboxylates such as dibutyltin dilaurate are benchmark high-activity catalysts and oxides such as dibutyltin oxide and dioctyltin oxide are especially important in high-temperature condensation and e-coat applications. ^{[3][5-9]}

¹ This article is intended as technical and historical background. It is not a substitute for current product- and jurisdiction-specific regulatory review.

2. Why organotin catalysts became important

Industrial organotin chemistry expanded rapidly in the mid-twentieth century as the chemistry of mono- and dialkyltin compounds became better understood and commercial polymer technologies developed. Their importance has historically been much greater than the small tonnage of tin involved because the catalyst can determine whether a process cures in minutes or hours, whether a coating survives an automotive bake, and whether a two-component material has a usable working time. ^{[1][2]}

The development of polyurethane chemistry created one of the largest uses. Organotin compounds became the traditional metal-catalyst benchmark for the alcohol-isocyanate reaction because they are highly active Lewis-acid catalysts. Modern mechanistic work shows that organotin dicarboxylates interact with alcohol to form an alkoxide-containing complex; the active complex then reacts with isocyanate, preferentially through nitrogen coordination in the modeled systems, forms an organotin carbamate and regenerates an active tin species as urethane is produced. ^{[3][4]}

Automotive e-coat provided a second strategically important role. Cathodic electrodeposition, commercialized in the 1970s as a major corrosion-protection technology, applies a waterborne primer uniformly to the electrically conductive vehicle body and then bakes the deposited film. Modern e-coat binders commonly use blocked-isocyanate cross-linking chemistry, and dialkyltin oxides have long been used to catalyse the bake cure. Dibutyltin oxide and dioctyltin oxide remain commercial important catalysts for aqueous cathodic electrodeposition of urethane coatings. ^{[6][10][11]}

3. Historical development

The history of organotin catalysts is best understood as the intersection of three developments: the growth of industrial organotin chemistry, the rise of polyurethane and silicone materials after the Second World War, and the move toward faster, more reproducible coating and adhesive production. The timeline below focuses on some of the more commercially important catalyst substances.

Period	Development	Why it mattered
1950s-1960s	Diorganotin carboxylates and oxides became established catalysts as polyurethane, silicone and polyester chemistry expanded. Dibutyltin diacetate (1067-33-0), dibutyltin dilaurate (77-58-7) and dibutyltin oxide (818-08-6) became representative high-activity materials.	Created practical cure rates for urethane, silicone and esterification chemistry and established organotin as a benchmark catalyst family.
1970s-1980s	Cathodic automotive e-coat became a major corrosion-protection technology. Dialkyltin oxides were incorporated into catalyst or pigment pastes to promote bake cure of blocked-isocyanate/active-hydrogen resin systems.	Linked organotin catalysts to one of the automotive industry's most durable primer technologies.
1980s-2000s	Catalyst families diversified: ketonate, mercapto and dioctyltin analogues were selected to tune latency, hydrolytic stability, cure profile and regulatory suitability.	Allowed formulators to match catalyst behaviour to pot life, one- or two-component packaging, bake temperature and end use.
2000s-present	CASE, RTV silicone and silane-terminated hybrid polymers expanded, while regulatory scrutiny of reproductive toxicity, mutagenicity and repeated-dose effects increased in Europe. Dioctyltin alternatives gained importance in some applications.	Modern catalyst selection now combines reaction engineering with substance-specific regulatory and stewardship requirements.

Table sources: Davies ^[1]; Ghazi et al. ^[2]; WHO/IPCS ^[5]; ACA ^[10]; commercial catalyst literature ^[6-9]

4. The catalyst substances used as catalysts

The substances below are all mono- or, predominantly, dialkyltin catalyst chemistries or reaction products/formulations based on them. They should not be treated as interchangeable merely because they contain tin. Alkyl substitution, ligand chemistry, physical form and formulation strongly affect activity, latency, hydrolytic stability, dispersibility and hazard classification.

CAS No.	Substance	Common shorthand	Principal catalyst roles
1067-33-0	Dibutyltin diacetate	DBTA / DBTDA	PU and CASE cure; RTV silicone and silane condensation; esterification/transesterification.
10584-98-2	Dibutyltin bis(2-ethylhexyl mercaptoacetate)	DBT mercaptoacetate	Delayed/controlled PU catalysis, especially adhesives, elastomers and foams; bake-cure coatings.
22673-19-4	Dibutylbis(pentane-2,4-dionato-O,O')tin	DBT acetylacetonate	Highly reactive PU catalyst; silicone/silane polycondensation.
77-58-7	Dibutyltin dilaurate	DBTL / DBTDL	Benchmark catalyst for PU, coatings, adhesives, sealants, elastomers; RTV silicone; silane cross-linking.
818-08-6	Dibutyltin oxide	DBTO	Cathodic e-coat cure; esterification/transesterification; alkyd/polyester resin manufacture.
93925-42-9	Tetraethyl silicate reaction products with dibutyltin diacetate	Dibutyltin siloxane	Alkoxy-RTV silicone cure; silane-terminated systems.
17586-94-6	Dioctyltin diacetate	DOTA / DOTAc	PU synthesis; RTV silicone and silane condensation; esterification/transesterification.
3648-18-8	Dioctyltin dilaurate	DOTL / DOTDL	Urethane cross-linking; silanol condensation; CASE applications.
870-08-6	Dioctyltin oxide	DOTO	Cathodic e-coat; high-temperature transesterification; coating-resin and specialty ester manufacture.

Sources: supplier technical literature and substance information. ^{[6-9][12-14]} Application descriptions are representative, not approvals for every formulation or jurisdiction.

5. How organotin catalysts work

5.1 Urethane formation

In polyurethane chemistry, organotin catalysts accelerate reaction between isocyanate groups and alcohol/polyol groups. Two descriptions have historically been used: direct insertion of isocyanate into a tin-oxygen bond, and Lewis-acid activation of the isocyanate or reacting complex. Current computational and experimental work on organotin dicarboxylates supports formation of an alcohol-derived alkoxide-containing complex as a dominant catalytic species, followed by coordination of isocyanate, carbamate formation and regeneration of the catalyst. The ligand matters: aliphatic isocyanates can be more sensitive than aromatic isocyanates to carboxylate ligand content and solvent environment. ^{[1][3][4]}

5.2 Silicone and silane condensation

RTV silicones and silane-terminated polymers cure through hydrolysis and condensation reactions that build Si-O-Si cross-links. A widely accepted mechanism for organotin dicarboxylates involves hydrolysis to a hydroxyl-carboxylate species, reaction with an alkoxysilane to form a stannasiloxane intermediate, and transfer of the silane functionality to terminal silanol groups. Repetition of the cycle forms a cross-linked network. This chemistry underlies classic condensation-cure RTV silicone and also supports moisture-curing hybrid sealants based on silane-terminated polyethers or polyurethanes. ^{[1][2]}

5.3 Esterification, transesterification and resin synthesis

Organotin oxides and carboxylates also catalyse reactions at carboxyl centres. Depending on the catalyst and medium, the tin compound may generate a tin alkoxide that increases alcohol nucleophilicity or act as a Lewis acid that increases carbonyl electrophilicity. Dibutyltin oxide can react with carboxyl-containing reactants to generate soluble distannoxane-like species; dioctyltin oxide provides analogous high-temperature catalytic functionality. These reactions are used in polyester and alkyd resin manufacture and in specialty ester and methacrylate chemistry. ^{[1][2][6]}

6. Where the catalyst is added in manufacturing

The essential point

Organotin catalysts are added before the reaction or cure step they are intended to accelerate. Depending on the process, they may be charged to a resin reactor, blended into the polyol or binder component, dispersed in an e-coat pigment/catalyst paste, or added during final formulation of a one- or two-component sealant or coating. They normally remain with the cured polymer or coating rather than being recovered as a separate process catalyst. ^{[5][11]}

6.1 Cathodic electrodeposition (e-coat)

In automotive and industrial cathodic e-coat, the catalyst is incorporated into the coating before the bath is used. Solid dialkyltin oxides such as dibutyltin oxide have historically been ground with a pigment-dispersing resin and water to make a catalyst-containing pigment paste. Dioctyltin oxide can be incorporated similarly. The pigment/catalyst paste is then blended with the main cationic binder, blocked-polyisocyanate cross-linker and deionized water to make the electrodeposition bath. The metal article (for example, an assembled vehicle body) is immersed, electrically coated, rinsed and then baked. The organotin catalyst becomes active during the oven bake and accelerates cross-linking of the deposited film.

^{[10][11][15]}

6.2 Polyurethane manufacture and CASE

For two-component polyurethane coatings, adhesives, sealants and elastomers, the catalyst is commonly added to the hydroxyl-functional or polyol side during formulation, so that the isocyanate side can be added later to start the final cure. In one-component isocyanate-terminated prepolymers, catalyst may be used during prepolymer synthesis and/or included in the final moisture-curing formulation. In foam manufacture, catalyst is metered with the polyol/additive stream before it meets the isocyanate; the catalyst package is chosen to balance urethane “gelling” against any water-isocyanate blowing reaction. ^{[1][5][7]}

For CASE products, the selected catalyst controls pot life, tack-free time, through-cure, hardness development and final network density. DBTL is a widely used benchmark. DBTA and the acetylacetonate catalyst provide high activity; the mercaptoacetate derivative can provide greater upfront delay and more

controlled back-end cure in PU adhesives, elastomers and foams. Dioctyltin carboxylates can serve similar functions where an octyltin chemistry is preferred. ^{[7-9][12][13]}

6.3 RTV silicone sealants

In two-component condensation-cure RTV silicone, one package can contain the hydroxyl-terminated polysiloxane while the second contains cross-linker and catalyst; cure begins after mixing. In one-component systems, the organotin catalyst is incorporated during dry formulation with the polymer and cross-linker, then protected from moisture in the sealed package. On exposure to atmospheric moisture, hydrolysis and condensation begin and the catalyst accelerates cross-link formation. Dibutyltin diacetate, dibutyltin dilaurate, dioctyltin diacetate and the dibutyltin-silicate reaction product are examples used in such silane/silicone chemistry. ^{[1][2][8][12][14]}

6.4 MS and SPUR hybrid polymers

MS polymers (silyl-terminated polyethers) and SPUR polymers (silyl-terminated polyurethanes) cure through moisture-triggered silane hydrolysis and condensation rather than through an isocyanate cure after application. The catalyst is therefore normally added during final sealant or adhesive formulation under controlled low-moisture conditions, together with fillers, plasticizers, adhesion promoters and moisture scavengers as required. It remains latent in the sealed package and becomes catalytically active as moisture enters after application. Dibutyltin acetylacetonate and the dibutyltin/silicate reaction product are commercially identified for 1K MS/STP systems; the broader organotin condensation chemistry also applies to SPUR-type materials. ^{[8][14]}

6.5 Polyester, alkyd and specialty-resin manufacture

For esterification and transesterification, organotin oxide or carboxylate catalyst is charged directly to the resin reactor with, or shortly after, the alcohol and acid/ester raw materials. The catalyst then operates throughout the heated condensation stage, often under water or alcohol removal. Dibutyltin oxide and dioctyltin oxide are particularly useful where high-temperature stability and low colour are important. ^{[1][6]}

7. Why these catalysts remain technically important

Organotin catalysts continue to be used because they combine high catalytic efficiency with formulation versatility. In polyurethane systems they can strongly favour the desired isocyanate-polyol reaction, allowing formulators to achieve fast cure and high conversion at modest addition levels. In e-coat, they help cross-linking within the tightly controlled automotive bake schedule. In silicone and hybrid sealants, they provide reliable moisture-cure kinetics over a broad range of ambient conditions. In esterification and transesterification, they offer strong Lewis-acid catalysis without relying on strongly corrosive mineral acids or bases. ^{[1][3][5-9]}

Their industrial importance is also connected to process control. Catalyst chemistry can be selected to provide immediate activity, controlled delay, or heat-triggered back-end cure. Mercapto-functional organotin catalysts use sulphur ligands to provide a blocking or delay effect that is overcome during an exothermic or baked cure. ^{[7][9]}

8. Why some organotin compounds have been restricted

Worldwide concern about “organotins” arose from several different histories. The most visible was the use of tributyltin (TBT) and related tri-substituted organotins as deliberately leaching biocides. For the listed dibutyltin and dioctyltin catalysts, the principal modern European drivers are reproductive toxicity,

mutagenicity or repeated-dose toxicity classifications, together with the potential for consumer or worker exposure. These hazard concerns have led to use restrictions, Candidate List identification for selected substances, export-notification obligations and increasingly strict workplace controls. ^[16-20]

8.1 Global controls on antifouling biocides

From the 1960s, TBT became highly effective in antifouling paints because it leached from ship hulls and prevented the attachment of algae, barnacles and molluscs. The same biological activity created widespread harm outside the target surface. Authorities documented persistence in the aquatic environment, high toxicity to aquatic organisms, shell deformation in oysters and endocrine-mediated reproductive effects such as imposex in gastropods. ^{[23][24]}

The International Maritime Organization adopted the International Convention on the Control of Harmful Anti-fouling Systems on Ships in 2001; it entered into force in 2008. The Convention prohibits application or re-application of organotin compounds that act as biocides in antifouling systems. This global action is a central reason the public associates organotins with bans, but TBT antifouling biocides are tri-substituted compounds used for intentional biological activity. They are not the mono- and dialkyltin substances used as catalysts.

8.2 EU restrictions on tri-substituted, dibutyltin and dioctyltin compounds

EU REACH Annex XVII entry 20 contains several layers of control. It prohibits organostannic compounds as biocides in free-association paint and in specified antifouling and industrial-water uses. It also restricts tri-substituted organostannic compounds in articles above the equivalent of 0.1% tin by weight. Separate provisions restrict dibutyltin (DBT) compounds in mixtures and articles supplied to the general public above that tin-equivalent threshold, subject to the legal scope and exemptions, and dioctyltin (DOT) compounds above the same threshold in specified consumer articles such as skin-contact textiles, gloves, footwear, childcare articles and certain other listed products. They do not amount to a universal ban on all industrial catalyst uses. ^{[16][17]}

8.3 Harmonised classifications and SVHC identification

Several organotin substances have EU harmonised classifications and some are included in the REACH Candidate List. ^[18-21] Candidate List status creates supply-chain communication and article-notification obligations and makes a substance eligible for future prioritisation for REACH authorisation. It does not itself prohibit industrial use. In ECHA's February 2026 prioritisation assessment, recommendation of both dioctyltin dilaurate-related substances and dibutyltin acetylacetonate for Annex XIV was postponed in that round. ^{[21][22]}

8.4 Occupational exposure

The European Commission has tasked ECHA with scoping organotin compounds for possible occupational exposure limit work. These developments reinforce the importance of closed handling, ventilation, personal protective equipment, spill prevention and substance-specific exposure assessment in catalyst manufacture and use. ^{[17][22]}

9. Outlook

Organotin catalysts helped make several modern materials and coating technologies commercially practical. They accelerated urethane formation, enabled reproducible RTV silicone cure, supported high-temperature polyester and ester chemistry, and became integral to the bake cure of cathodic e-coat one of the automotive industry's most important corrosion-protection technologies. Their history is therefore not a

single application story but a pattern of using highly efficient tin-centered Lewis-acid chemistry wherever cure rate, selectivity and process reliability are critical. ^{[1][5][10]}

The future of the organotin catalysts will be shaped by the same combination of factors that now governs all specialty catalyst selection: performance at real manufacturing conditions, full-substance toxicology, worker and environmental exposure controls, compatibility with lower-VOC and waterborne formulations, and the regulatory status of the specific substance and end use. In some applications, dioctyltin catalysts are replacing traditional dibutyltin chemistry; in others, organotin catalysts remain technically difficult to match without reformulation or changes in cure conditions. ^{[7-9][12-14]}

For GOSC and the downstream value chain, the central stewardship principle is therefore substance-specific and use-specific management: preserve the technical benefits of effective catalysis where use is permitted, while controlling exposure and ensuring that regulatory decisions distinguish among organotin structures, functions and actual use scenarios.

References

- [1] Davies, A.G. "Organotin compounds in technology and industry." *Journal of Chemical Research* 2010, 181-190. doi:10.3184/030823410X12698696585509.
- [2] Ghazi, D.; Rasheed, Z.; Yousif, E. "A Review of Organotin Compounds: Chemistry and Applications." *Archives of Organic and Inorganic Chemical Sciences* 3(3) (2018). doi:10.32474/AOICS.2018.03.000161.
- [3] Devendra, R.; Edmonds, N.R.; Sohnel, T. "Investigations of catalysis of urethane formation using organotin dicarboxylate." *Heliyon* 6 (2020) e04074. doi:10.1016/j.heliyon.2020.e04074.
- [4] Sardon, H. et al. "Synthesis of Polyurethanes Using Organocatalysis: A Perspective." *Macromolecules* 48 (2015): 3153-3165. doi:10.1021/acs.macromol.5b00384.
- [5] World Health Organization / IPCS. Concise International Chemical Assessment Document 73: Mono- and Disubstituted Methyltin, Butyltin, and Octyltin Compounds. Sections 4.2.1-4.2.4 on catalyst uses. https://iris.who.int/bitstream/handle/10665/43549/9241530731_eng.pdf
- [6] PMC Organometallix. FASCAT Catalyst Product Portfolio and 8000 Series product information: DBTO (818-08-6), DBTL (77-58-7), DOTO (870-08-6), DOTL (3648-18-8). <https://fascat.com/product-portfolio/>
- [7] TIB Chemicals. TIB KAT 202 technical data sheet (dibutyltin dilaurate formulation), December 2025.
- [8] TIB Chemicals. Product information for TIB KAT 226, dibutylbis(acetylacetonate) (CAS 22673-19-4). https://tib-chemicals.com/en/product/tin-chemicals/tib-kat-226_en
- [9] TIB Chemicals. Product information for TIB KAT 321, dibutyltin bis(2-ethylhexyl mercaptoacetate) (CAS 10584-98-2). https://tib-chemicals.com/en/product/tib-kat-321_en
- [10] Lamb, D.M. "A Brief History of Automotive Coatings Technology." *CoatingsTech*, American Coatings Association, February 2017.
- [11] US Patent 5,176,804 / EP 0436135: catalyst pastes containing dibutyltin oxide for cathodic electrodeposition coatings.
- [12] TIB Chemicals. Product information for TIB KAT 229, dioctyltin diacetate (CAS 17586-94-6). https://tib-chemicals.com/en/product/tib-kat-229_en
- [13] TIB Chemicals. TIB KAT 416 product information, dibutyltin-based catalyst formulation (CAS 93925-42-9) for alkoxy RTV and 1K MS/STP systems. https://tib-chemicals.com/en/product/tib-kat-416_en
- [14] PMC Organometallix. FASCAT 8201/8202 product information, dioctyltin oxide and dioctyltin dilaurate. <https://fascat.com/fascat-8000-series/>
- [15] Example of modern e-coat formulation: EP 3 689 979 B1, pigment dispersion paste containing dioctyltin oxide catalyst.
- [16] European Commission. Commission Regulation (EU) No 276/2010 amending REACH Annex XVII entry 20 for organostannic compounds.
- [17] European Chemicals Agency (ECHA). REACH Annex XVII Entry 20 and organostannic substance/group information; current text accessed September 2026.

- [18] European Commission. Regulation (EU) 2017/776 (10th ATP to CLP), harmonised classification of dibutyltin dilaurate (CAS 77-58-7).
- [19] ECHA Committee for Risk Assessment. CLH opinions/registry entries for dibutyltin diacetate (CAS 1067-33-0) and dibutyltin oxide (CAS 818-08-6), opinion adopted 2025.
- [20] ECHA Candidate List. Dibutylbis(pentane-2,4-dionato-O,O')tin (CAS 22673-19-4), included 25 June 2020 for toxicity to reproduction.
- [21] ECHA Candidate List. Dioctyltin dilaurate and related C12 fatty acyloxy dioctyltin derivatives, including CAS 3648-18-8, included 19 January 2021 for toxicity to reproduction.
- [22] ECHA. Prioritisation assessment results of Candidate List substances, 2 February 2026; Annex XIV recommendation postponed in that round for dioctyltin dilaurate-related substances and dibutyltin acetylacetonate.
- [23] International Maritime Organization. "International Convention on the Control of Harmful Anti-fouling Systems on Ships (AFS Convention)."
- [24] US Environmental Protection Agency. "Ambient Water Quality Criteria for Tributyltin (TBT) - Final," EPA 822-R-03-031, 2003/2004.

About GOSC

The [Global Organotin Stewardship Council](#), established in 2021, aims to enhance understanding of the intrinsic health and environmental properties of organotin compounds while highlighting their benefits. It actively communicates this information to stakeholders, ensuring scientific consistency and clarity.

Additionally, GOSC represents the major organotin manufacturers and technology sector in order to support Members and market organizations in their engagement globally with policy makers and regulatory authorities. The Global Organotin Stewardship Council (GOSC) consists of manufacturers of organotin manufacturers: Galata Chemicals, Gulbrandsen, Nitto Kasei Co., Ltd., PMC Group, Reagens S.p.A, Songwon Industrial Group, and TIB Chemicals AG.

GOSC monitors and responds to global Regulations on Organotins with the following objectives:

- Develop scientific and socioeconomic data to accurately assess organotin-based substances.
- Demonstrate that organotin-based substances can be safely handled.
- Assess if Organotin-based substances are easily replaced in the applications in which they are used and where they show outstanding performance or are critical in certain applications.
- Recommend justifiable regulatory action and/or appropriate risk management measures for organotin based substances.
- Promote the most appropriate regulatory management option for any initiative that may be triggered on organotin-based substances and develop regulatory consensus on it.